

REMARKS

Claims 1-3 and 5-20 are now present in this application, with new claims 8-20 being added by the present Preliminary Amendment. Claim 4 has been cancelled without prejudice or disclaimer of the subject matter contained therein. It should be noted that the amendments to original claims 1-3 and 5-7 of the present application are non-narrowing amendments, made solely to place the claims in proper form for U.S. practice and not to overcome any prior art or for any other statutory considerations. For example, amendments have been made to broaden the claims; remove reference numerals in the claims; remove/change any phrases unique to European practice; remove multiple dependencies in the claims; and to place claims in a more recognizable U.S. form, including the use of the transitional phrase "comprising" as well as the phrase "wherein". Other such non-narrowing amendments include placing apparatus-type claims (setting forth elements in separate paragraphs) and method-type claims (setting forth elements in separate paragraphs) in a more recognizable U.S. form. Again, all amendments are non-narrowing and have been made solely to place the claims in proper form for U.S. practice and not to overcome any prior art or for any other statutory considerations.

CONCLUSION

Accordingly, in view of the above amendments and remarks, an early indication of the allowability of each of claims 1-3 and 5-20 in connection with the present application is earnestly solicited.


Should there be any outstanding matters that need to be resolved in the present application, the Examiner is respectfully

requested to contact Donald J. Daley at the telephone number of the undersigned below.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 08-0750 for any additional fees required under 37 C.F.R. § 1.16 or under 37 C.F.R. § 1.17; particularly, extension of time fees.

Respectfully submitted,

HARNES, DICKEY & PIERCE, P.L.C.

By:   
Donald J. Daley, Reg. No. 34,313

P.O. Box 8910  
Reston, Virginia 20195  
(703) 668-8000

DJD/bof

ABSTRACT OF THE DISCLOSURE

A radically crosslinkable liquid composition is for producing a polyacrylamide-based hydrogel layer. The composition includes at least one comonomer with reactive linker groups and at least one optional softener in addition to the monomer precursor of the polyacrylamide, the crosslinking agent, and the radical initiator(s).

Description

DT05 Rec'd PCT/PTO 07 FEB 2005

**SUBSTITUTE SPECIFICATION****RADICALLY CROSSLINKABLE HYDROGEL COMPRISING LINKER GROUPS**

[0001] This application is the national phase under 35 U.S.C. § 371 of PCT International Application No. PCT/DE2003/002548 which has an International filing date of July 29, 2003, which designated the United States of America and which claims priority on German Patent Application number DE 102 36 461.3 filed August 8, 2002, the entire contents of which are hereby incorporated herein by reference.

**Field of the Invention**

[0002] The present invention generally relates to radically crosslinkable liquid compositions for producing a hydrogel based on polyacrylamide.

**Background of the Invention**

[0003] So-called biochips are increasingly being used in modern biological analysis technology as well as in medical diagnostics. Biochips are mostly planar carrier systems made from glass or plastic, the surface of which is equipped with a two-dimensional recognition layer comprising biological recognition molecules. A known example for a biochip of this type is the optical DNA chip which can be read-out, ~~said the~~ biochip being described by F. Hänel, H.P. Saluz in BIOforum 9/99, pages 504-507.

[0004] The use of three-dimensional immobilization layers for biological recognition molecules is expedient in order to increase the sensitivity of this type of biochip and to optimize the reproducibility of the measurement results. Schleicher & Schuell GmbH use a three-dimensional immobilization layer for a product called FAST™ Slides DNA chips, in which capture oligos are immobilized in a three-dimensional nitrocellulose membrane

(Schleicher & Schuell, Biomolecular Screening, Catalogue 2001  
(International Edition)).

**[0005]** One problem with the technical realization of corresponding immobilization layers is firstly the desire to achieve a cost-effective method for applying the layers onto the chips or the transducer systems. The immobilization systems made from liquid precursors are dripped onto a suitable base, dispensed, hydroextracted or imprinted thereon. Thermal polymerization and/or crosslinking, drying processes or photochemical polymerization processes and/or crosslinking processes are chosen to solidify the layers.

**[0006]** Ph. Arquint describes a photo-crosslinked hydrogel based on a crosslinked polyacrylamide for this type of application ('Integrated Blood Gas Sensor for pO<sub>2</sub>, pCO<sub>2</sub> and pH based on Silicon Technology (Dissertation, Ph. Arquint. University of Neuchatel, Switzerland, 1994)).

**[0007]** Hydrogels play a significant role in the chemical and/or biological analysis and particularly in the realization of chemosensors and biosensors. Their function is to realize a watery environment in a mechanically stable form at the same time as guaranteeing the exchange of materials in a predominantly watery environment. By selecting the chemical composition concerning the components and their ratios among one another, the properties of the hydrogels, such as the water content, swelling behavior, mechanical stability etc. can be varied over large areas.

**[0008]** In his dissertation, Ph. Arquint describes a method whereby polyacrylamide hydrogels are applied to silicon wafers and phototechnically structured by means of an approximately semiconductor compatible method. Nevertheless one decisive problem exists with the technology described:

**[0009]** One disadvantage of the system described by Arquint, i.e the hydrogel precursor, can be seen in that no reactive linker groups

are available in the crosslinked layer, said linker groups allowing chemical or biological recognition molecules to be coupled for analytical applications.

**[0010]** In Nucleic Acids Research, 1966, Volume 24, No. 16, pages 3142-3148 Timofeev et al. describe a chemically modified radically crosslinked polyacrylamide, which can be used, among other things, for the immobilization of capture oligos. Amino and aldehyde groups are used as coupling groups in the hydrogel. Aldehyde and/or amino functionalized capture oligos can be immobilized covalently on these coupling groups subject to reductive reaction conditions. ~~This means that~~thus, an additional reduction step is required using a reduction ~~means~~device/method, in addition to the actual coupling reaction between amino and/or aldehyde groups or vice versa. Further methods described by Timofeev et al. for the chemical activation of the crosslinked polyacrylamide similarly require additional reaction steps in the polymer matrix.

#### **SUMMARY OF THE INVENTION**

**[0011]** ~~An~~The object of an embodiment of the present invention is thus to provide a radically crosslinkable acrylamide-based hydrogel system, which contains a comonomer which enables the covalent coupling of correspondingly modified biomolecules, in other words, chemical or biological recognition molecules with compatible linker groups, across a reactive linker group in a simple, rapid reaction step, without the use of any additional chemicals.

#### **DETAILED DESCRIPTION OF THE EXEMPLARY EMBODIMENTS**

**[0012]** The subject-matter of an embodiment of the present invention is consequently a radically crosslinkable liquid composition for producing a polyacrylamide-based hydrogel layer, which stands out in that the composition comprises at least one comonomer with reactive linker groups and at least one optional softener in addition to the monomer precursor of the polyacrylamide, the crosslinking agent, and the radical initiator(s).

[0013] A water-swellaable hydrogel is achieved after manufacturing the layer and the thermal and/or photo crosslinking, said hydrogel containing reactive linker groups to immobilize chemical or biological recognition molecules for analytical or diagnostic applications.

[0014] The monomer precursor of the polyacrylamide is based on acrylamide and methylenebisacrylamide, whereby two monomer chains are connected to one another as with Arquint. By varying the concentration of the crosslinking agent methylenebisacrylamide, dimethylacrylic acid ester, such as tetraethylene glycol dimethacrylate, for example, the mesh size of the hydrogel can be easily adjusted.

[0015] The comonomer with reactive linker groups is preferably selected from the group comprising maleic acid anhydride and/or glycidyl methacrylate. The softener is preferably monoethylene glycol, diethylene glycol or triethylene glycol. By optimizing the softener content in the composition, the dried precursor layer can be optimized in its polymerization behavior.

[0016] The composition is preferable in a polar solvent which can be mixed with water, preferably dimethyl formamide. The processing viscosity can be easily adjusted by varying the solvent content.

[0017] The composition according to an embodiment of the invention offers numerous advantages for the production of hydrogels, in particular those which are to be used for producing immobilization layers. The precursor components can be mixed in a widely variable mixing ratio. The viscosity of the composition can be easily adjusted. A good layer formation is guaranteed during which no phase separation takes place. The layer is sufficiently transparent for light for the photoinitiation.

[0018] Crosslinking density and water swelling capacity can be arbitrarily adjusted. The auxiliary components such as the softener etc, can be easily washed out after the crosslinking. The adhesion

to the substrate surface can be strengthened by means of conventional adhesion promoter systems based on silicon for example.

[0019] Exemplary embodiments being thus described, it will be obvious that the same may be varied in many ways. Such variations are not to be regarded as a departure from the spirit and scope of the present invention, and all such modifications as would be obvious to one skilled in the art are intended to be included within the scope of the following claims.